

# On the safe side

## SCHOTT Radiation Shielding Glass RD 30®

### A good, clear view

SCHOTT RD 30® is drawn, clear flat glass that contains lead and is used as radiation shielding glass. It has the usual surface traits of drawn glass.

### Not only for use in mammography

RD 30® was developed especially for use in mammography workstations with weak X-rays (a lead equivalent of 0.5 mm Pb at 56 kV is commonly used here). Nevertheless, RD 30® also has a lead equivalent of 0.5 mm Pb at a higher tube voltage (up to 150 kV) and can therefore also be used in workplaces for material testing and at all other workplaces with weak X-ray radiation.

To ensure safe handling of the glass, we recommend that you follow our "Instructions on Installing, Cleaning and Caring for Radiation Shielding Glass."

### Properties and processing options

The SCHOTT Radiation Shielding Glass RD 30® is delivered in processed or refined form.

The following processing options are available with RD 30®:

- Special formats, also with edge processing and bored holes
- Safety glass (tempered)
- Laminated glass
- Curved glass
- Printed/painted glass



### Delivery forms – RD 30® Radiation Shielding Glass

- Single pane glass: 6 mm (max. delivery dimensions: 2,350 x 1,500 mm [92.5" x 59.1"])
- Laminated glass: > 6 mm (consisting of 2 x 3 mm RD 30®)

### Examples of applications

SCHOTT RD 30® Radiation Shielding Glass can be used in many areas of medicine, science and industry, in particular in X-ray rooms, operating rooms, irradiation stations, dental practices, radiology practices, laboratories and materials testing.

### RD 30®: Lead equivalents in mm Pb and delivery dimensions of single pane glass

Thickness d mm	Attenuation equivalent in mm Pb and delivery dimensions:						Max. weight kg/m <sup>2</sup>	Max. dimensions mm x mm
	50 kV	56 kV	76 kV	80 kV	110 kV	150 kV		
6.0 ± 0.25	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	≥ 0.5	20	2,350 x 1,500 (92.5" x 59.1")

### Technical data on RD 30® (single pane glass)

#### Optical properties

Refractive index  $n_e$  at 20°C (annealed at 40°C/h) 1.579  
Light transmission factor (d = 6.0 mm) 90.5%

#### Chemical properties

Hydrolytic class according to DIN ISO 719 HGB 3  
Lead oxide content (PbO) ≥ 22%  
Total heavy metal oxide content ≥ 23%

#### Mechanical characteristics

Density in g/cm<sup>3</sup> (delivery condition) ≥ 3.13

#### Other properties

Glass thickness 6.0 mm  
Evaluated sound insulation  $R_w$   
Spectral adaptation values C and  $C_{tr}$   
 $R_w(C; C_{tr}) = 34 (-2; -2)$  dB

SCHOTT North America, Inc.  
5530 Shepherdsville Road  
Louisville, KY 40228  
USA  
Phone +1 (502) 657-4417  
info.architecture@us.schott.com

www.us.schott.com/rd-30

**SCHOTT**  
glass made of ideas