

Glass 8230

Technical Data

| | | | |
|--|--|-------|--|
| Glass Type/Application | Intermediate sealing glass Sealing to Glass 8229 and Glass 8330 | | |
| <hr/> | | | |
| Physical Data (approx. value) | Coefficient of mean linear thermal expansion $\alpha(20^\circ\text{C}; 300^\circ\text{C})$ (ISO 7991) | 2.7 | 10^{-6}K^{-1} |
| | Transformation temperature T_g (ISO 7884-8)..... | 570 | $^\circ\text{C}$ |
| | Glass temperature at viscosity η in $\text{dPa} \cdot \text{s}$ | | |
| | 10^{13} (annealing point) (ISO 7884-4)..... | 590 | $^\circ\text{C}$ |
| | $10^{7.6}$ (softening point) (ISO 7884-3)..... | 915 | $^\circ\text{C}$ |
| | 10^4 (working point) (ISO 7884-2)..... | 1425 | $^\circ\text{C}$ |
| | Stress-optical coefficient K (DIN 52314)..... | - | $10^{-6}\text{mm}^2 \cdot \text{N}^{-1}$ |
| | Density ρ at 25°C | 2.19 | $\text{g} \cdot \text{cm}^{-3}$ |
| | Modulus of elasticity E (Young's modulus) | - | $10^3\text{N} \cdot \text{mm}^{-2}$ |
| | Poisson's ratio μ | - | |
| | Thermal conductivity λ_w at 90°C | - | $\text{W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$ |
| | Log of the electric volume resistivity ($\Omega \cdot \text{cm}$) | | |
| | at 250°C | - | |
| | at 350°C | - | |
| | t_{k100} | 255 | $^\circ\text{C}$ |
| | Dielectric constant ϵ for 1 MHz at 25°C | - | |
| | Dielectric loss factor $\tan \delta$ for 1 MHz at 25°C | - | 10^{-4} |
| | Refractive index n_d ($\lambda = 587.6 \text{ nm}$) | - | |
| <hr/> | | | |
| Chemical Resistance | Hydrolytic resistance (ISO 719) | Class | - |
| | Acid resistance (DIN 12116) | Class | - |
| | Alkali resistance (ISO 695) | Class | - |
| <hr/> | | | |
| The heavy metal content for the elements lead, cadmium, mercury and hexavalent chromium is below 100 ppm | | | |

PT_TTS_1040 GB

Business Unit Tubing / 9/2017

SCHOTT
glass made of ideas