ROBAX® TrueView When it looks like there is no glass at all it's ROBAX® TrueView.





ROBAX® TrueView

ROBAX® uncoated

Technical Data	
Maximum usable area	1,800 x 1,070 mm
Glass thickness	4 und 5 mm
Recommended application	Gas fireplaces
Effect of coating	Reduces reflections from the area surrounding the fireplace, offers the best possible view of the fire
Reflection	\leq 1 % (for the wavelength range from 380 to 780 nm)
Coated side	Both sides coated
Color impression of coating	In reflection slightly blue-green, in transmission without color
Shape	Flat cut-to-size panels
Surface structure	Both sides smooth
Decoration	No
Cleaning	Soft cloth and standard window glass cleaner
Temperature resistance (glass-ceramic substrate with TrueView coating)	500 °C (932 °F) = 600 hours

